

DATE: 10-10-2022

TEST NUMBER: 0405131

CLIENT: Go Green - Turf Evolutions

TEST CONDUCTED: ASTM F1551 Water Permeability of Synthetic Turf Systems and Permeable Bases, DIN 18-035



PRODUCT NAME: Heatmaxx 47
 DESCRIPTION OF PRODUCT TESTED: G35261B - 7210 Turf

GENERAL PRINCIPLE

The test procedure is used to determine the flow rate of rainfall through a material. A volume of water is poured through the surface and timed. Calculations are then made on the inches of water that would pass through the substrate per hour. The sample was tested as received.

TEST RESULTS

IDENTIFICATION	RESULTS
Heatmaxx 47	1205.70 Inches/Hour
	5.14 Sec/6" Zone
	393.00 Gal/min/yd ²

APPROVED BY: *Gary Colburn*

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.